

PATENT ABSTRACTS OF JAPAN

(11)Publication number : 2005-105206
(43)Date of publication of application : 21.04.2005

(51)Int.Cl.

C08L 69/00
C08K 3/34
C08K 5/41
C08K 5/42
C08L 27/12

(21)Application number : 2003-343309

(71)Applicant : ASAHI KASEI CHEMICALS CORP

(22)Date of filing : 01.10.2003

(72)Inventor : MIYAMOTO AKIRA
SHIBUYA KAZUHIRO

(54) FLAME RETARDANT AROMATIC POLYCARBONATE RESIN COMPOSITION

(57)Abstract:

PROBLEM TO BE SOLVED: To provide a flame retardant aromatic polycarbonate resin composition which is excellent in melt stability, heat resistance, and surface gloss, and is free from a bromine-based flame retardant or a phosphorus-based flame retardant.

SOLUTION: The aromatic polycarbonate resin composition comprises (A) 100 pts.wt. of an aromatic polycarbonate, (B) 0.01-1 pt.wt. of a silicate compound, (C) an organic acidic compound and/or an aromatic acidic compound derivative, (D) 0.001-1 pt.wt. of at least one metal salt selected from an organic alkali metal salt and an organic alkaline earth metal salt, and (E) 0.01-1 pt.wt. of a fluoropolymer, wherein the component (C) has such a pts.wt. that the component (B) and the component (C) may be mixed to give a pH value of 4.0-8.0 as measured according to JIS K5101.

LEGAL STATUS

[Date of request for examination]

[Date of sending the examiner's decision of rejection]

[Kind of final disposal of application other than the examiner's decision of rejection or application converted registration]

[Date of final disposal for application]

[Patent number]

[Date of registration]

[Number of appeal against examiner's decision of rejection]

[Date of requesting appeal against examiner's decision of rejection]

[Date of extinction of right]

Copyright (C); 1998,2003 Japan Patent Office